

URKI-FLEX

AIR DRYING "HIGH QUALITY" SYNTHETIC ENAMEL

URKI-SYSTEM

CONVERTER: 6026 / CONV U-FLEX

RELATION PASTE / CONV.: 25/75

Edition: 020 2011/11
 Cod: 6902600000.00000.020

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Suitable for painting of commercial vehicles, agricultural machinery and public works, etc.
 Excellent paint because of its easy application, good filling power, levelling, quick drying, high gloss and resistance outdoors, to water, detergent and petrol splashes.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	0,95 - 1,11
Grinding Fineness (μ)	20 - 30
Supply viscosity at 20°C	70-77 KU (Stormer)
%Solids content (weight / volume)	49 - 59 % weight; 41 - 44% volume.
V.O.C. (g/l)	569 (Ready to use)
Type of product	Special Alcidic
Colour	URKI-SYSTEM

SURFACE PREPARATION

On rust-free steel and thoroughly degreased, first prime with F-29 Synthetic Zinc Phosphate.
 If a higher resistance to corrosion is required, use F-809 Zinc Phosphate Synthetic Primer.

APPLICATION INSTRUCTIONS

The accelerator for Synthetics BESA-FILM may be added in a proportion of 200 cc. for 1 litre of enamel. In this case the dilution with URKISOL 170 is reduced to 10-15 %.

Brush or Roller: Only for small surfaces, diluted up to 5 % of URKISOL 222/B.



20"
 FORD nº 4



URKISOL 222
 5-10 %



URKISOL 170
 30-35 %



35-45 my



Touch free 30'
 Tack free 4-5 h.

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	10 - 11 (40 my)
Gloss 60°-60°	> 90 %
Second layer	After 24 hours

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.
 Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.