

URKI-NOX
ANTI-RUST SINGLE COAT

URKI-SYSTEM

CONVERTER: 6033 / CONV U-NOX
RELATION PASTE / CONV.: 25/75

Edition: 021 2017/05

Cod: 6903300000.00000.021

APPLICATION

"USE ONLY IN INDUSTRIAL FACILITIES"

Suitable for the painting of structures, pipes, tanks, industrial vehicles, agricultural and public works machinery, etc. Outstands for its application easiness, filling power, extensibility and quick drying. Good resistance outdoors, water, detergents and petrol spattering.

Salt Spray Test > 250 hours.

URKI-NOX meets the requirements for category C3 Low in accordance to ISO 12944-2 on shotblasted steel Sa 2 ½ certified by an independent approved Laboratory.

PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,10 - 1,30
Grinding Fineness (µ)	15 - 20
Supply viscosity at 20°C	75 - 85 KU (Stormer)
%Solids content (weight / volume)	60 - 67 % weight; 48 - 52 % volume.
V.O.C. (g/l)	567 (Ready to use)
Type of product	Modified Alkyd / Zinc Phosphate
Colour	URKI-SYSTEM

SURFACE PREPARATION

On Steel, deoxidize and degrease.

If a higher rust protection is required use F-809 Zinc Phosphate Primer.

APPLICATION INSTRUCTIONS



20-30"
FORD nº 4



URKISOL 222
5-10 %



URKISOL 170
35-40 %
Ø 1.4-1.6 mm



35-45 my



4-5 h. Tack free



URKISOL 170
20-30 %
0,011-0,013"



URKISOL 170
20-30 %
0,011-0,013"

FEATURES OF DRY FILM

Theoretical yield (m ² /l)	12 - 13 (40 my)
Gloss 60°-60°	60 - 85 %
Second layer	After 72 hours

STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.

Can life: **2 years** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.